



AGS COMPANY
P.O. Box 729
Muskegon, MI 49443
231-733-2101 Fax: 231-733-1784
info@agscompany.com

CUT-EASE STICK LUBRICANT

DESCRIPTION: The material covered by this specification is a solidified lubricant, molded in stick form. It consists of a specially-blended wax composition, plasticized with mineral oil, and containing film strength additives. Composition does not dry out, exude oil, or crumble, and is sufficiently dry to prevent catching excessive dirt and dust under normal conditions.

APPLICATION Used for lubrication of exposed friction surfaces. Facilitates assembly of various parts. When applied to metal, wood, rubber, plastic, glass, and other surfaces, prevents squeaks, wear, and sticking. CUT-EASE is used like a crayon in application to surfaces. It can also be applied by melting in a glue pot or similar equipment. Apply molten CUT-EASE by dipping, brushing, or with saturated cloth.

Packaging

CE-16	Large Stick - approximately 2" diameter x 10-3/4" long
CE-16DA	Cardboard tube with metal push-bottom and plastic cap on each end.
CE-16HG	
CEP-16	
CEK-30	Small Stick - approximately 1" diameter x 4-3/8" long Stick wrapped with self-adhesive label

Properties	Appearance and Color	Green Solid
	Texture	Microcrystalline
	ASTM Penetration @ 77°F (50g. Needle)	5.0 - 10 mm
	ASTM melting Point	150°F +/- 5°
	Moisture	Nil
	Ash (as Sulfate)	Nil
	Free Alkali (as NaOH)	Nil
	Film Strength (Falex test):	700 to 800 pound Jaw Load
	Test Pins	Vee Blocks
	SAE 3135 Steel	AISI 1137 Steel
	Hardness Rb 87-91	Hardness Rc 20-24
	Surface Finish - 10 RMS max.	Surface Finish - 10 RMS max.

Meets Chrysler standard MS-1481

P.O. Box 729, Muskegon, MI 49443, U.S.A.
Toll Free 800-253-0403 Toll Free in Michigan Canada 800-735-0403
Local Calls (231) 733-2101 FAX (231) 733-1784